

**Table 2-2 Diffusion Coefficients of Gold in Lead (3 MIM Modes) (mm<sup>2</sup>/s) 10<sup>-3</sup>**

T°C	ISOLATING	LATCHED	3 mm	QUELD-I & QUESTS	0.1 Hz (1998)
354				2.27	
390		2.30			5.89
390			3.04		
428				3.03	
441				3.40	
492	1.93	3.94			
530				4.23	
542				4.40	
592	2.51				
684	3.07			5.80	
715					
785	3.58				
835				7.95	